

MAPEFLOOR CPU+/MF

High-performance self-smoothing polyurethane cement mortar from 3 to 6 mm



DESCRIPTION

Mapecfloor CPU+/MF is a polyurethane-cement self-smoothing mortar, trowel-applied in 3 to 6 mm thickness, developed by MAPEI's Research Laboratories, microbe-resistant and easy to sanitize for the protection of industrial floors, featuring high chemical and mechanical performance and thermal shock resistance up to +80°C, with operating temperatures range from -20°C to +70°C, depending on the thickness.

TECHNICAL CHARACTERISTICS

Mapecfloor CPU+/MF provides a protective resin system for industrial floors featuring:

- depending on the thickness applied, resistance to thermal shocks due for example to spillage of hot liquids:
3 mm: -10°C up to +60°C
4 mm: -15°C up to +70°C
6 mm: -25°C up to +80°C;
- fast hardening;
- smooth finishing;
- high chemical resistance against acids, bases, saline solutions, solvents, hydrocarbons in general. For more details, refer to the related chemical resistance table;
- high resistance to impact and abrasion;
- impermeability to liquids in general;
- odourless during application and hardening;
- low VOC content and emission;
- does not allow bacterial growth;
- complies with the requirements according to EN 13813 "Screed material and floor screeds - Screed material - Properties and requirements", which defines the requirements to be applied to materials for screeds used in the construction of internal floors;
- complies with the principles defined in EN 1504-9 ("Products and systems for the protection and repair of concrete structures: definitions, requirements, quality control and evaluation of conformity. General principles for the use of products and systems"), and the minimum requirements required by EN 1504-2, coating (C), according to PI, MC, PR, RC, IR principles ("Surface protection systems for concrete").

ADVANTAGES

- Fulfills HACCP requirements.
- Complies with all Indoor Air Comfort Gold emission requirements for indoor flooring systems, including AgBB in Germany, M1 in Finland and Afsset in France, BREEAM, CAM, Singapore Green Label and Global Green Tag. Classified A+, the best class for the lowest emissions.
- Complies with standards applied in the foodstuffs sector EN 1186, EN 13130 and prCEN/TS 14234, as well as the Decree of Consumer Goods that represent the conversion of European directive 89/109/EEC, 90/128/EEC and 2002/72/EC regarding contact with foodstuffs.
- Hygienic and sanitizable; certified according to ISO 4628-1 Riboflavin test for cleaning validation.
- Resistant to fungi and bacteria, certified according to ISO 846.
- Does not allow microbial growth according to ISO 22196.
- Fast return to service.
- Ease for warehousing management; components A, B and **Mapecolor CPU+** are common to whole **Mapefloor CPU+** product range.
- Sustainability: it can contribute to LEED credits. EPD (Environmental Product Declaration) compliant.

WHERE TO USE

Mapefloor CPU+/MF is mainly used to create smooth polyurethane-cement based systems, with a light no-slip property, or as base layer for rough multi-layer systems (**Mapefloor System CPU+/DP 4**) for industrial floors especially in dry or even occasionally wet, for short periods, production and logistic areas, where a durable, resistant and easy to clean and sanitize surface is required.

Mapefloor CPU+/MF is typically used in the chemical and pharmaceutical, textile and tanning industries, canning in general, sugar refineries, dairies, wineries and beverage companies in general, meat and fish processing, production and storage areas of food companies in general, commercial and industrial kitchens, freezing rooms and wherever high mechanical and chemical spillages and contact to hot liquids resistances are requested.

COLOURS

Mapefloor CPU+/MF must be mixed with the specific **Mapecolor CPU+** pigment available in grey, beige, red, green, ochre, blue and orange colour. Please, always refer to the Mapei Technical Service for a detailed assessment of the most suitable system and colour for the specific case. The colour helps to define the overall performance of the system.

RECOMMENDATIONS

- Do not apply **Mapefloor CPU+/MF** on wet substrates or on concrete younger than 7 days.
- Do not dilute **Mapefloor CPU+/MF** with solvents or water.
- Do not apply **Mapefloor CPU+/MF** on dusty or crumbly substrates.
- Do not apply **Mapefloor CPU+/MF** on substrates contaminated by oil, grease, or dirt in general.
- Do not apply **Mapefloor CPU+/MF** on not properly prepared substrates.
- Do not mix partial quantities of the components to prevent mistakes in the mixing ratios which would cause incorrect hardening of the product.
- Do not expose the mixed product to heat sources.
- Do not apply **Mapefloor CPU+/MF** on ceramic substrates or stone materials in general with no appropriate specific preparation of the laying surface.
- **Mapefloor CPU+/MF** exposed to UV rays could lead to noticeable colour changes; this phenomenon does not affect the performance of the coating in any way.
- The colour of **Mapefloor CPU+/MF** can also change in case of contact with certain chemicals; the colour variation itself is not an indication of chemical aggression on the coating.
- Remove as soon as possible any chemicals in contact with **Mapefloor CPU+/MF**.
- For cleaning use suitable equipment and detergents depending on type of dirt to be removed.

- Protect **Mapecfloor CPU+/MF** from water for at least 24 hours after the application.

APPLICATION PROCEDURE

Substrate characteristics

Substrates must be solid, compact, stable, sound, clean, and properly designed for static and dynamic loads foreseen in the operating conditions. The flatness must be defined by the needs of use. At the time of application, compressive strength of the concrete or cementitious mortar used for the repair must be higher than 25 N/mm² and the direct tensile strength at least 1.5 N/mm².

The substrate surface must appear visually dry. There must be no capillary rising damp as well.

In the case of substrate such as ceramic tiles, natural stones, or old resin coatings, they must be perfectly stable and anchored to the substrate, intact, sound, and clean. These substrates require specific preparation methods for the laying surfaces. In the case of old resin coatings, it is recommended to also perform a compatibility test with the new system to be applied.

Substrate preparation

The surface of the floor must be prepared with specific mechanical equipment such as for example shotblasting or milling machine, to remove all traces of dirt, any contamination for the entire thickness concerned, cement laitance, crumbly or detached parts and make the surface rough and absorbent.

Any defects such as holes, pitting, cracks, etc. must be repaired using, for example, **Primer SN** possibly filled with quartz sand or thixotropic agent like **Additix PE** or with **Mapecfloor JA** or **Mapecfloor JA Fast** depending on the width and depth of the defects and cracks.

For the reconstruction of heavily degraded areas and joints, the filling of large depressions, repairs, or minimal localized changes to slopes, etc., please contact the Technical Service.

Before proceeding with the application of the material, the surface dust must be carefully vacuumed.

Anchor grooves

The anchoring grooves on the concrete must be made with a suitable mechanical joint saw. The dimensions (depth and width) must be approximately double the thickness of **Mapecfloor CPU+/MF**.

They must be provided along the perimeter of the area, near all the vertical lines such as walls and pillars, around the drainage channels and wells, on the thresholds of the doors, around the feet of the machinery, in general along each free edge and the interruptions of the installation, such as joints that clearly define the end of the working day and the beginning following one.

The maximum distance between parallel grooves must not exceed approximately 15 meters. If it exceeds this measure, it will be necessary to make intermediate cut.

In case concrete has not fully completed its hygrometric shrinkage, it is advisable to make the anchor grooves also along the cracks control joints. It will make possible to seal the joint in case the shrinkage crack appears in the joint (therefore also on **Mapecfloor CPU+/MF**) even without removing part of the floor, as the entire area straddling the joint is already well anchored.

Temperature

To avoid the condensation on the surface, the substrate temperature must be at least 3°C above the dew point. The relative humidity of the air must be lower than 80%. The ambient temperature must be between +10°C and +30°C.

In case of application at temperature above +25°C, store the material in a sheltered spot at a lower temperature. This will allow to get longer pot life and get the application simpler even at high temperatures. In case of temperature below +15°C, store the material in a warmer place (heated room temperature) to avoid the risk of too high viscosity of the mix making the application harder and turning into a potential problem of aesthetics effect.

Application of the primer

Mapecfloor CPU+/MF must be applied on a substrate with no surface porosity to prevent pinholes in the hardened product. For such reason a preliminary layer of **Mapecfloor CPU+/Primer** must be applied.

Alternatively, **Primer SN** fully broadcast with quartz sand **Quartz 0.9** can be used as well but only for fully cured and dry substrates with a moisture content < 4% and when no thermal shocks are expected during the service life of the floor.

In case of rough surface, apply a scratch coat using **Mapefloor CPU+/MF** to even the surface. For further information about preparation, mixing, consumption and application details of **Mapefloor CPU+/Primer** and **Primer SN**, please read the related Technical Data Sheets.

Product preparation

Shake the packs containing the liquid components A, B and **Mapecolor CPU+** pigment. Pour two packs of component A and two packs of **Mapecolor CPU+** into a clean bucket and mix for a few seconds until a homogeneous mixture is obtained. Then add two packs of component B and mix again with a suitable low-speed electric mixer until completely blended. Then slowly and gradually add one pack of component C, continuing to mix for at least three minutes until a homogeneous mixture is obtained. We recommend the use of specific low-speed mixers. At temperatures lower than +23°C this time could be slightly longer. Only mix whole packs of components A, B, C and **Mapecolor CPU+** to prevent potential mistakes in the mixing ratios which could compromise the entire system.

Product application

Immediately after mixing, pour all mixed **Mapefloor CPU+/MF** on the floor and spread it evenly to the required thickness with a straight or serrated trowel or a squeegee fitted with thickness rulers. It is advisable to proceed with the installation of the product in such a way as to ensure that the material that has just been poured can be connected to the one already laid when the latter is still fresh and workable. This way the signs of conjunction will be minimized. Immediately after spreading, it is necessary to use a spike roller several times to remove any air trapped during mixing and help the material smoothing. Apply the mix within the useful pot life indicated in the table. The higher the temperature, the lower the pot life; the lower the temperature, the higher the pot life.

SYSTEMS

Mapefloor CPU+/MF can be applied both as a self-smoothing and as the basecoat of the multilayer defined profile system (**Mapefloor System CPU+/DP 4**). For the whole description of **Mapefloor System CPU+/DP 4** see the relevant system Technical Data Sheet.

CONSUMPTION

As scratch coat 1 mm thickness:

Mapefloor CPU+/MF:	approx. 1.7 kg/m ²
---------------------------	-------------------------------

As self-smoothing layer:

Mapefloor CPU+/MF 3 mm:	approx. 5.5 kg/m ²
Mapefloor CPU+/MF 4 mm:	approx. 7 kg/m ²
Mapefloor CPU+/MF 6 mm:	approx. 10 kg/m ²

The consumption is influenced by the roughness and absorption of the substrate as well as by the environmental and working conditions of the job site.

TOOLS CLEANING

Equipment used to prepare and apply **Mapefloor CPU+** product range must be cleaned with thinner for polyurethanes immediately after use. Once the product has hardened, it can only be removed mechanically.

FLOOR CLEANING

The first cleaning after laying **Mapecolor CPU+/MF** must only be carried out after the product has completely hardened. Early washing could lead to the formation of stains/shading due to the surface not yet perfectly closed and still partially absorbent.

For periodic and extraordinary washing, use suitable and specific machines, equipment and detergents for the type of stains and dirt to be removed.

PACKAGING

Mapecolor CPU+ Component A: 2 kg pack

Mapecolor CPU+ Component B: 2.16 kg pack

Mapecolor CPU+/MF Component C: 20 kg bag

Mapecolor CPU+: 0.23 kg pack.

Warning: Product consists of two packs of component A plus two packs of component B plus one sack of component C and two packs of **Mapecolor CPU+**.

STORAGE

12 months in the original sealed packaging and kept in a dry and sheltered place at temperatures between +10°C and +30°C. Components A and B can be damaged by frost. **Mapecolor CPU+/MF** part C is sensitive to humidity.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Instructions for the safe use of our products can be found on the latest version of the Safety Data Sheet, available from our website www.mapei.com.

When the product reacts, it generates considerable heat. After mixing components A, B and C, we recommend applying the product as soon as possible and to never leave the container unguarded until it is completely empty.

PRODUCT FOR PROFESSIONAL USE.

TECHNICAL DATA (typical values)

PRODUCT IDENTITY

	Comp. A	Comp. B	Comp. C	Mapecolor CPU+
Colour:	Milky white	Dark brown	White grey	Grey, beige, red, green, ochre, blue, orange
Appearance:	Liquid	Liquid	Powder	Paste
Density:	1-1.05 g/cm ³	1.2 g/cm ³	–	1.30-1.60 g/cm ³
Bulk density:	–	–	1.80-1.95 g/cm ³	
Viscosity at +23°C:	200-600 mPa·s (# 2 - rpm 20)	100-160 mPa·s (# 1 - rpm 50)	–	6 000-25 000 mPa·s (# 6 – rpm 20)

APPLICATION DATA

Mixing ratio:	2xA / 2xB / 1xC / 2x Mapecolor CPU+ : 2x2.0 / 2x2.16 / 1x20 / 2x0.23
Colour of the mix:	Grey, beige, red, green, ochre, blue, orange
Consistency of the mix:	Fluid
Density of the mix:	1,700 kg/m ³
Pot life at +23°C:	15 min
Temperature of the surface:	From +10°C to +30°C

FINAL PERFORMANCE at +23°C and 50% R.H.

Tack free:	2-4 h
Ready for traffic at:	- Recoating: 12 h - Light traffic: 24 h
Complete hardening:	4-5 days
Shore D hardness after 28 days (DIN 53505):	83
Slip resistance (EN 13036-4):	Class I (wet internal surfaces) Class II (dry internal surfaces)
Modulus of elasticity by compressive strength (EN 13412):	4306 MPa
Coefficient of linear thermal expansion (EN 1770):	$5.35 \cdot 10^{-5} \text{ K}^{-1} \alpha_m$
Determination of characteristics by flexural strength (EN ISO 178):	4488 MPa
Depth of water penetration under positive pressure (EN 12390-8):	No penetration (5 bar / 3 days)
Adhesion strength (EN 13892-8):	$\geq 2 \text{ N/mm}^2$

Essential characteristics	Test method	Requirements according to EN 13813 for cement screeds	Typical values
Abrasion resistance BCA:	EN 13892- 4	$\leq \text{AR6}$	AR0.5
Compressive strength:	EN 13892-2	From C5 to C80	C50
Flexural strength:	EN 13892-2	From F1 to F50	F15
Permeability to water:	EN 1062-3	Declared value	$w < 0.1 \text{ kg}/(\text{m}^2 \cdot \text{h}^{0.5})$ (Class III)
Chemical resistance:	EN 13529	CR group number (from 1 to 15 a) and class (1 or 2)	Shore D reduction < 50% CR9, CR10, lactic acid 10-90 Vol% (class 2, change of colour, clearer) CR11, CR12 (Class 2)
Reaction to fire class:	EN 13501-1	Declared value	B _{FL} -s1

ESSENTIAL CHARACTERISTICS FOR CE MARKING ACCORDING TO EN 1504-2 – TAB. ZA.1d; ZA.1e; ZA.1f; ZA 1g (coating C, principles PI-MC-PR-RC-IR)

Essential characteristics	Test method	Requirements	Typical values
Abrasion resistance (TABER test): Note: testing methods for flooring systems according to EN 13813 are also acceptable	EN ISO 5470-1	Loss in weight less than 3000 mg with an H22 abrasive wheel /1,000 cycles /1,000 g load	<3000 mg
Permeability to CO ₂ :	EN 1062-6	$S_D > 50 \text{ m}$	>50 m
Permeability to water vapour:	EN ISO 7783-1-2	Class I: $S_D < 5 \text{ m}$ (permeable to water vapour) Class II: $5 \text{ m} \leq S_D \leq 50 \text{ m}$ Class III: $S_D > 50 \text{ m}$ (impermeable to water vapour)	Class II
Capillary absorption and permeability to water:	EN 1062-3	$w < 0.1 \text{ kg}/\text{m}^2 \cdot \text{h}^{0.5}$	$w < 0.1 \text{ kg}/\text{m}^2 \cdot \text{h}^{0.5}$
Resistance to thermal shock (1x):	EN 13687-5	Rigid systems with traffic $\geq 2 \text{ N/mm}^2$	$\geq 2 \text{ N/mm}^2$

Resistance to severe chemical attack – Class I: 3 days with no pressure: – Class II: 28 days with no pressure: – Class III: 28 days with pressure: We recommend using test liquids for the 20 classes indicated in EN 13529, which cover all types of the most-commonly used chemical agents. Other test liquids may be agreed upon between those interested in the tests	EN 13529	Reduction of hardness less than 50% when measured according to the Buchholz method (EN ISO 2815) or the Shore method (EN ISO 868), 24 hours after removing the coating material from immersion in the test liquid	Shore D reduction < 50% Groups 9, 10, lactic acid 10-90 Vol % (Class II, change of colour, clearer) Groups 11, 12 (Class II)
Impact resistance:	EN ISO 6272-1	No cracks or delamination after loading Class I: ≥ 4 Nm Class II: ≥ 10 Nm Class III: ≥ 20 Nm	Class II
Direct tensile adherence test:	EN 1542	Average (N/mm ²) Crack-bridging or flexible systems without traffic: ≥ 0.8 (0.5) ^{b)} with traffic: ≥ 1.5 (1.0) ^{b)} Rigid systems ^{c)} without traffic: ≥ 1.0 (0.7) ^{b)} with traffic: ≥ 2.0 (1.5) ^{b)}	≥ 2 N/mm ²
Reaction to fire class:	EN 13501-1	Euroclasses	B _{FL} -s1

CLEANROOM TESTING (CSM standard)

Characteristics	Test method	Test parameters	Classification
Cleanability (Riboflavin test)	ISO 4628-1	0 = excellent 1 = very good 2 = good 3 = weak 4 = very weak 5 = none	1/very good
Fungi and bacteria resistance	ISO 846	0 = excellent 1 = very good 2 = good 3 = weak 4 = very weak 5 = none	2/good

Indoor Air Comfort GOLD – VOC Emission

French VOC Regulation
(Decree of March /April 2011 modified in February 2012)



French CMR components
(Regulation of April/May 2009)

Pass

Italian CAM Edilizia
(DM23.06.2022 n.256, GURI n.183 06/08/2022)

Pass

AgBB
(Regulation AgBB/DIBt)

Pass

Belgian Regulation
(Royal decree of May 2014)

Pass

Indoor Air Comfort
(Indoor Air Comfort 8.0 of June 2022)

Pass

Indoor Air Comfort GOLD
(Indoor Air Comfort GOLD 8.0 of June 2022)

Pass

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation.

The most up-to-date TDS can be downloaded from our website www.mapei.com.

ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.

All relevant references for the product are available upon request and from www.mapei.com

TECHNICAL SPECIFICATION

Supply and installation of odourless, self-smoothing polyurethane-cement mortar for industrial floors, trowel-applied from 3 to 6 mm thickness, to create a microbe resistant and sanitizable protection with high chemical and mechanical resistances, resistant to thermal shocks up to +80°C and for freezing rooms down to -25°C (such as **Mapecolor CPU+/MF** by MAPEI S.p.A.), coloured with the suitable pigment available in grey, beige, red, green, ochre, blue and orange colours (such as **Mapecolor CPU+** by Mapei S.p.A.), after applying the polyurethane-cement primer by roller or rubber squeegee for the saturation of the porosity of the substrate (such as **Mapecolor CPU+/Primer** by MAPEI S.p.A.).

The hardened material must have the following characteristics:

Shore D hardness at 28 days (DIN 53505)	83
Abrasion resistance BCA (EN 13892- 4)	≤ 10 µm
Slip resistance (EN 13036-4)	> 40 unit (wet internal surfaces) > 40 unit (dry internal surfaces)
Depth of water penetration under positive pressure (EN 12390-8)	No penetration (5 bar / 3 days)
Flexural strength (EN 13892-2)	≥ 15 N/mm ²
Compressive strength (EN 13892-2)	≥ 50 N/mm ²
Impact resistance (EN ISO 6272)	10 Nm
Bond strength at 28 days (EN 13892-8)	≥ 2 N/mm ²
Capillary absorption and permeability to water (EN 1062-3)	w < 0.1 kg/m ² ·h ^{0.5}
Chemical resistance (EN 13529)	CR9, CR10, CR11, CR12 (Class 2)
Permeability to CO ₂ (EN 1062-6)	S _D > 50 m
Permeability to water vapour (EN ISO 7783-1-2)	5 m ≤ S _D ≤ 50 m
Resistance to thermal shock (1x) (EN 13687-5)	≥ 2 N/mm ²
Reaction to fire class (EN 13501-1)	B _{FL} -s1
VOC Emission (EN 16516)	Indoor Air Comfort Gold including AgBB in Germany, M1 in Finland and Afsset in France, BREEAM, CAM, Singapore Green Label and Global Green Tag. Classified A+, the best class for the lowest emissions
Riboflavin test (ISO 4628-1)	Very good
Does not allow microbial growth (ISO 22196)	Good

Resistant to fungi and bacteria (ISO 846)	Good
Complies with standards applied in the foodstuffs sector EN 1186, EN 13130 and prCEN/TS 14234, as well as the Decree of Consumer Goods that represent the conversion of European directive 89/109/EEC, 90/128/EEC and 2002/72/EC regarding contact with foodstuffs	
Fulfills HACCP requirements	
Contributes to obtaining LEED credits, EPD (Environmental Product Declaration) compliant	

Mapei S.p.A.

Via Cafiero, 22, 20158, Milano



+39-02-376731



www.mapei.com



mapei@mapei.it

8990-7-2024-II en (IT)

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

