

# weber.kol porselen

## Tile adhesive for glazed porcelain, porcelain and granite ceramics

Technical Data Sheet

Issued on : 15.11.2017

Revision No: 005

### ■ Description

High performance, cement based tile adhesive with reduced slip and extended open time for granite, porcelain ceramics and glazed porcelain.

### ■ Advantages

- Safe application with large sizes granite, porcelain and glazed porcelain tiles.
- Improved performance on tile application on existing tile
- Application on plaster substrates.

### ■ Range of application

- Used for fixing ceramic, granite ceramic and glazed porcelain at interior walls and floors and exterior floors.

### ■ Application substrates

- Interior walls:
  - Cement based render,
  - Gypsum board, gypsum plaster (**weber.prim AS** (**weber.prim art** applied)),
  - Concrete,
  - Existing tile (**weber.prim TG 5** applied).
- Interior floors:
  - Cement based screed,
  - Concrete floor,
  - Existing tile (**weber.prim TG 5** applied).
- Exterior floors,
  - Cement based screed,
  - Concrete.
- Please consult us for all other application substrates.

### ■ Limits of application

- Not applicable on metal surfaces (**weber EP 800** should be used).
- Not applicable on prefabricated or floor heating floors (**weber.kol flex konfor konsantre** or **weber.kol flex extra** should be used).
- Not applicable on exterior walls and exterior façades (**weber.kol flex konfor konsantre** or **weber.kol flex extra** should be used).

### ■ Application properties

- Pot life: max. 4 hours,
- Open time: max. 30 minutes,
- Adjustability: max. 20 minutes,
- Time required for grouting: 24 hours.
- Time required for foot traffic: 24 hours.
- Application thickness: 3 to 10 mm (one or both sides applications).

### ■ Performance

- High initial tensile adhesion strength:  $\geq 1 \text{ N/mm}^2$
- High tensile adhesion strength after water immersion:  $\geq 1 \text{ N/mm}^2$
- High tensile adhesion strength after heat aging:  $\geq 1 \text{ N/mm}^2$
- High tensile adhesion strength after freeze-thaw cycles:  $\geq 1 \text{ N/mm}^2$

- Extended open time tensile adhesion strength:  $\geq 0,5 \text{ N/mm}^2$  after not less than 30 min.
- Heat resistance: between  $-30 \text{ }^\circ\text{C}$  and  $+60 \text{ }^\circ\text{C}$ .  
*These values were obtained as a result of laboratory tests and they are valid for 28 days performance of finished applications. Values may vary due to differences on job-sites.*

### ■ Reference standards

- TS EN 12004 /C2 TE class
- CE
- Public Works Pos No: 04.380/009  
*Please see current "weber solution guide" for the classification introduced by TS EN 12004 norm about tile adhesives.*

### ■ Attention points

- White **weber.kol porselen** should be used for light colored ceramic, glazed porcelain and similar coatings.
- Never add foreign materials.
- All tools should be cleaned with water before drying after the application.

### ■ Preparation of substrates

- The surface should be dry, smooth and durable, plasters thinner than 3 mm on the substrate should be scraped and cleaned thoroughly.
- Very porous substrates should be wetted and waited until the water layer disappears as the floor will remain damp.
- Important deformations or holes on the substrate should be repaired with **weber.rep MA 200** minimum 24 hours before the application of **weber.kol porselen**
- Local repairs thinner than 7 mm can be done by use of **weber.kol porselen**.

### ■ Conditions of application

- Ambient temperature is between  $+5 \text{ }^\circ\text{C}$  and  $+35 \text{ }^\circ\text{C}$ .
- It should not be used on substrates which are frozen or melting or have the risk of frost within 24 hours.
- Avoid application under direct sunlight, strong wind or hot surfaces.

### ■ Application

- Average 7,25-7,75 lt water and 25 kg **weber.kol porselen** should be mixed with low-speed mixer preferably or trowel until no more lump will remain.
- After aging **weber.kol porselen** for 5 minutes, it should be mixed for further 15-30 second before application.
- The mortar should be applied on the substrate and its thickness should be adjusted with steel notched trowel. Tooth size of trowel should be adjusted according to dimensions of tile and smoothness of application substrate.
- Mortar should be applied on both application substrate and behind the ceramics with below-mentioned sizes (back buttering).

- For granite ceramic, glazed porcelain, natural composed stone, etc.,
  - Interior floor applications: 500 cm<sup>2</sup>
  - Interior wall applications: 120 cm<sup>2</sup>
- For ceramic, tile, etc.
  - Interior wall and floor applications: 1100 cm<sup>2</sup>
  - All exterior floor applications.
- For good adhesion, force should be applied by means of rubber hammer and air should be ejected.

### ■ Consumption

Tile dimensions	Notched trowel	Consumption
120 cm <sup>2</sup>	6x6x6 mm.	One-sided adhesion 4 kg./m <sup>2</sup> Double-sided adhesion 5-6 kg./m <sup>2</sup>
120 cm <sup>2</sup> and 500 cm <sup>2</sup>	8x8x8 mm.	One-sided adhesion 5 kg./m <sup>2</sup> Double-sided adhesion 6,5 kg./m <sup>2</sup>
500 cm <sup>2</sup> and 3600 cm <sup>2</sup>	10x10x10 mm.	one-sided adhesion 5,5 kg./m <sup>2</sup> double-sided adhesion 7-8 kg./m <sup>2</sup>

### ■ Packaging

25 kg bag (64 bags in pallet, 1600 kg).

### ■ Pallet size

107 x 107 cm.

### ■ Color

White and grey.

### ■ Application tools

Hand mixer, trowel, rubber hammer, steel notched trowel.

### ■ Shelf life

1 year as of the production date in dry and moisture-free environment provided that packages will not be opened.  
Package should be kept tightly closed when not in use.

- > The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures.  
> **Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş.** is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.



Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş.  
Kemalpaşa OSB Mah. Kuyucak Yolu Sokak No: 284 • 35730 Kemalpaşa • İzmir • Türkiye  
Tet +90 (232) 397 07 00 • www.weber.com.tr • info@weber.com.tr • Çözüm hattı: 444 6 990

